

Fabric	Alt Mesh Count	Type of Weave	Thread Diameter	Mesh Openings	Percentage Open Area	Thickness	Ink Volume	Recommended Tensions	Available Bolt Widths - Unmarked widths may be available by custom order							
									cm	115	135	140	216	254	305	343
Mesh Count	Alt Mesh Count	PW/TW	microns	microns	%	microns	cm3/m2	Newtons	inch	45	53	65	85/90	100	120	135
LX 80	LX 80SS	PW	55	263	68%	80	63	13-20			○	○				
LX 135	LX 135S	PW	48	140	55%	78	43	16-25			○	○				
LX 150	LX 150S	PW	48	121	51%	78	40	18-28			○	○				
LX 180	LX 180S	PW	48	93	44%	77	34	20-29				○				
Standard Polyester S Mesh:																
80-W	80-S - White	PW	71	247	60%	120	72	16-25		○		○	○			
110-W	110-S - White	PW	71	160	48%	114	55	23-36		○	○	○	○			
135-W	135-S Yellow	PW	48	140	55%	78	43	18-29				○	○	○		
150-W	150-S White	PW	48	121	51%	77	39	18-29				○				
150-Y	150-S Yellow	PW	48	121	51%	77	39	18-29		○	○	○				
160-Y	160-S Yellow	PW	48	111	49%	79	39	18-29		○	○	○				
180-Y	180-S Yellow	PW	48	93	44%	74	33	22-35		○	○	○	○			
200-Y	200-S Yellow	PW	48	79	39%	73	28	24-37				○				
225-Y	225-S Yellow	PW	40	73	42%	59	25	18-29			○	○				
310-Y	310-S Yellow	PW	30	52	40%	45	18	16-25		○	○	○				